Sedoso[™]X4 (Extra Fine)

| PARTICLE SIZE SPECIFICATION SEDOSO X4 | | | | |
|---------------------------------------|-------|-----------|-----------------|--|
| SIZE | | | ALLOWABLE | |
| MICRON | MM | U.S. MESH | PERCENT PASSING | |
| 90 | 0.09 | 170 | 99.5-100 | |
| 75 | 0.075 | 200 | 98-100 | |
| 45 | 0.045 | 325 | 77-93 | |
| TEST METHOD: ASTM C136-06 | | | | |

PHYSICAL DESCIPTION

Naturally-occuring foamed volcanic glass; white

| OTHER PROPERTIES SEDOSO X4 | | | |
|------------------------------|-----------------------|--|--|
| MEAN PARTICLE SIZE (Microns) | HARDNESS (Mohs Scale) | | |
| 16-18µm | 6 | | |




LEFT: Sedoso™ (spanish for *silky*) is an extra fine pumice finish/polish grit. RIGHT: Showcasing this kind of wood-grained beauty comes down to getting the finish right. FAR RIGHT: If the finish matters, then the polishing grit matters.



(208) 766-4777 • www.hesspumice.com

Mining and refining the purest commercial deposit of white pumice on the planet.





PACKAGING OPTIONS

- 1 or 2.5 lb resealable bags
- 20 lb [9 kg] box
- 45 lb [20.4 kg] production bags
- 2000 lb [907 kg] super sacks (palleted)
- Bulk shipped in rail car or tractor trailer

ORDER

- Samples, small quantities, and single production bags (up to 3): order direct from the **PumiceStore.com**
- Partial pallets, full pallets, truckloads: contact us at **sales@hesspumice.com** or call **208-766-4777**

PUMICE TECHNICAL DATA

Chemical analysis, physical properties, and other common data shared by all Hess Pumice grades are detailed on back.

Hess Pumice Technical Data

CHEMICAL ANALYSIS AND PHYSICAL PROPERTIES

Chemical Name: Amorphous Aluminum Silicate

TYPICAL ANALYSIS

GENERAL PROPERTIES

- Silicon Dioxide: 76.2%
- Aluminum Oxide: 13.5%
 · H
- Ferric Oxide: 1.1%
- Ferrous Oxide: 0.1%
- Sodium Oxide: 1.6%
- Potassium Oxide: 1.8%
- Calcium Oxide: 0.8%
- Titanium Oxide: 0.2%
- Magnesium Oxide: .05%
- Moisture: <1.0%
- Crystalline Si0₂: None Detected

- Appearance: White powder
 Hardness (MOHS): 6
- pH: 7.2
- Radioactivity: None
 - Softening Point: 900 degrees C
- Water Soluble Substances: 0.15%
- Loss on Ignition 5%
- GE Brightness: 84
- Specific Gravity: 2.2
- Reactivity: Inert (except in the presence of calcium hydroxide or hydrofluoric acid)

DESCRIPTION

Amorphous (non-crystalline) in structure and composed primarily of aluminum silicate, pumice is a naturally calcined volcanic glass foam consisting of highly vesicular strands permeated with tiny air bubbles. It is these frothy, friable glass vesicles that, when carefully refined to various grades, give pumice its unique and infinitely useful qualities.

NOTES

- Chemical analysis and physical properties provided are common to all raw Hess pumice grades.
- Grade Variety. The natural, hardyet-friable character of our pumice combined with our crushing and screening expertise allow us to offer pumice grades and grade blends down to 3 microns.
- Safe to Use. No hazardous crystalline structure: testing for crystalline silica (airborne particles of respirable size) finds no measurable Crystalline Silica (Si0₂) present. Free of heavy metals, pesticides, nano-particles, allergens. Certified organic input material.
- **Purity**: As the result of centuries of wave action from a now-extinct inland sea, our pumice is remarkably pure. Our mine grades are typically comprised of 98% pumice and 2% other igneous minerals, which are not removed through our mining processes.
- **Storage**: Keep dry and protected from the elements until use.



(208) 766-4777 www.**hesspumice.com**

